

Polomyx Airless

PRODUCT DATA SHEET



FINISH DESCRIPTION

Polomyx Airless / Building Standard Multicolor

Polomyx Airless gives you the great look and reparability of Polomyx with a smaller particle size that allows for easy airless spray application. So when the job calls for multicolor, but the timing and the budget demand speed and economy, Polomyx Airless is the ideal finish for you.

FEATURES

BENEFITS

Finish	Textured Multicolor
Formulation	Waterbase / 100% Acrylic
Colors	Thousands of colors available.
Easy Application	Airless Spray Equipment.
Lead Time	3-5 days for stock colors. 7-10 for custom colors.
Waterbased / Low VOC	Meets all environmental requirements.
Warranty	5 - Year manufacturer's warranty against adhesion failure if product
Class A fire rated	Like all Zolatone finishes, Polomyx Airless is Class A fire rated.

WHERE TO SPECIFY POLOMYX AIRLESS

Zolatone Finishes are designed for vertical wall surfaces yet can be applied to imperfect substrates like Block, Tile, Metal, etc. along with Architectural Elements, Features and Ceilings.

Corporate Spaces

Corridors
Offices
Lobby areas
Conference rooms
Cafeterias
Lunch rooms
Bathrooms
Stairwells

Educational Facilities

Corridors
Offices
Lecture halls
Auditoriums
Gymnasiums
Locker rooms
Bathrooms
Dormitories

Healthcare Facilities

Corridors
Offices
Waiting areas
Examination rooms
Meeting rooms
Cafeterias
Bathrooms
Stairwells

Other Applications

Theaters
Exercise rooms
Pool areas
Escalator areas
Elevator areas
Passenger terminals
Baggage claim areas
Parking areas

Suitable Substrates / Primed sheetrock (level 3+), previously painted surfaces, concrete block, metal, ceramic tile, glazed block, imperfect surfaces and others. (All substrates must be prepped and primed with un-tinted white primer.)

SURFACE PREPARATION

Surfaces should be clean, dry and free of dust, grease, wax or other contaminants. Gloss surfaces need to be deglossed or scuff sanded prior to priming and finish application. Stains should be spot primed with a quality Stain Blocking primer before general priming. All primers need to be un-tinted white primer.

APPLICATION INFORMATION

System Components	Un-Tinted White Primer (Sealing, Bonding, or Other), Zolatone Polomyx Airless.
Method	Spray only. Polomyx Airless should be sprayed using airless spray equipment according to manufacturer's published installation instructions. Consult application guide or visit www.zolatone.com regarding proper spray equipment, set up and technique. DO NOT SPRAY WITH CONVENTIONAL SPRAY EQUIPMENT
Tinting	Do not tint primer. Do not tint material.
Thinning	Product is ready for use. Consult application guide or call (800) 765-6699 for details on evaluating and adjusting material viscosity.
Dry Time	Air dry @ 70°F and 50% relative humidity. To touch in 2-4 hours. Full cure in 7-10 days.

TECHNICAL INFORMATION

Coverage Rate:	Up to 160 sq. ft. per gallon depending upon color, pattern size, surface porosity, surface texture and method of application.
Dry Film Thickness:	Average 2.5 - 3.0 mils.
Solid by Volume:	29-32%
Specular Gloss:	Maximum of 10 @ 60° Angle
DOT Shipping Class:	Not regulated
VOC Content:	30 g/L
Solids by Weight:	38-42%
Service Temp:	Min. 50°F Max. 85°F
Flash Point:	Not applicable
Caution:	Protect from freezing. Do not apply when temperature of paint or surface is below 50° F.
Shelf Life:	6 months from ship date

PERFORMANCE TESTING

A. V.O.C.: Less than 30grams/liter (waterbase acrylic formula)	ASTM-3960
B. ContinuousColor™: Complete integration of color particles within and throughout the paint finish.	
C. Fire Rating: Class "A" Fire Rated	ASTM E-84
D. Scrubability: 4,500+ cycles (to system failure).	ASTM D-2486
E. Abrasion Resistance: 101 mg loss / 1000 cycles / 1000 gram weight.	ASTM D-4060
F. Accelerated Weathering: 500 hours. No chalking or change in film integrity. Very good color retention. Excellent water resistance.	ASTM G-53
G. Stain Resistance: Resistant to the following: catsup, butter, orange juice, soda, vegetable oil, motor oil and betadine.	ASTM D 1308
H. Washability: No Change in Specular Gloss (100 cycles).	Fed Std 141B Method 6141
I. Resistance to Common Cleaners and Disinfectants including: soapy water, liquid cleansers, mild-abrasive cleansers, 70% isopropyl alcohol solutions. Film Not Affected.	ASTM D-1308
J. Adhesion Over Primed Surfaces: Good adhesion.	ASTM D-3359
K. Hardness-Pencil: HB	ASTM D-3363
L. Flexibility Test: No cracking of film when bent around a 1/8" mandrel.	ASTM D-522
M. Resistance of Emulsion Paint in the Container to attack by Micro-Organism. No Growth	ASTM D-2574
N. Permeability: 7.5 - 11.4 perms (with SP97 or SP203 primer)	ASTM D-1653
O. Mildew and Fungal Resistance: No growth.	ASTM D-2574

PERFORMANCE TESTING

P. Bacterial Resistance: No growth.	ASTM D-3456
Q. Flashpoint: D.O.T. / OSHA - Not Regulated	ASTM D-56
R. Specular Gloss: Maximum of 10 @ 60°.	ASTM D-523
S. Impact Resistance: Pass: 60 lbs.-in, no visible cracking (over Bonderite Steel Panel)	ASTM D-2794
T. Lifting: Polomyx Airless can be recoated, painted or covered with sheet goods without stripping.	Fed Std 141B Method 6552
U. Hiding power of paints by reflectometry: Not less than .96 contrast ratio. Passes LEED requirement of minimum .95 contrast ratio.	ASTM D-2805

WARRANTY

Master Coating Technologies warrants the Zolatone components of this finish system against manufacturing defect for a period of five years from the date of application when applied to a wall surface according to manufacturer's current printed instructions. Manufacturing defect is defined to be a failure of the coating system to adhere to a wall surface when applied according to manufacturer's printed instructions, and does not include subsequent failure or damage caused by exogenous factors such as substrate failure or defect, sharp objects, persons, or acts of God. In the event of a failure resulting from manufacturing defect, the product will be replaced. Master Coating Technologies shall have no obligation to or otherwise participate in labor or other costs associated with replacing the product.



Zolatone Interior Finishes
2777 Eagandale Boulevard
Eagan, MN 55121
www.Zolatone.com
800.765.6699